

TECHNICAL DATA SHEET N° 205

CODE 1.564.

creative ard lime carrara

Carrara marble effect mineral coating

GENERAL PROPERTIES

Decorative coating composed of mineral extenders & modified lime putty it let get a spatulated finish "carrara marble" effect.

CREATIVE ARD LIME CARRARA let obtain prestigious finishes really solid and velvety matt, with a good water resistance and a great water vapour permeability.

Ideal to be used on traditional plaster work and with a cement basis, it is specifically recommended for interior decoration of architectural buildings and for the restoration of historic centers.

INSTRUCTIONS

Surface preparation

The product is ideal for the interior application. Surfaces must be perfectly clean, brushed & sound.

- Bare mineral surfaces: maintain surfaces wet especially when the subbase is particularly absorbent or exposed to high temperatures.
- Mineral surfaces with distemper paintwork: clean thoroughly, stucco any imperfections with LITOSTUCCO. Sand & seal the whole surface with a layer of ISOLEX W or ARDFIX. Allow 4 hrs & apply CREATIVE FONDO.
- Interior surfaces with washable emulsion paintwork: clean throughly, stucco any imperfections, sand and dust. Seal the stuccoed areas with a layer of ISOLEX W or ARDFIX. Allow 4 hrs & apply CREATIVE FONDO.

Application

- Do not dilute: the product is ready to use.
- Apply two or more filling coats, at intervals of at least 6 hrs, with a stainless steel float until the surface is even. This procedure can be carried out on the final coat, before the product dries, using a drawdown blade. The final shade depends greatly on the weather and support absorption.
- Apply CREATIVE ARD LIME CARRARA in a temperature range between +5°C and +35°C.
- Store at ambient temperature (+5°/+40°C) in the original sealed containers.
- Protect against frost.
- If stored for a long period, CREATIVE ARD LIME CARRARA tends to thicken, so stir energetically before applying.
- CREATIVE ARD LIME CARRARA is one of the WIZARD tinting systems' product.
- Avoid contact with skin and eyes, in case of contact wash immediately with water.
- Use gloves and protective eyewear.
- Use the products in compliance with current Health and Safety Regulations. Dispose of spent material/containers according to the same. Refer to the MSDS for further details.

TECHNICAL PROPERTIES

TYPE OF BINDER	Modified seasoned lime putty with synthetic binder in aqueous emulsion
SPECIFIC WEIGHT	1800 ± 50 g/l
VISCOSITY AT 20°C	90.000 ±140.000 cP
DRYING AT 20°C *	12-14 h
FRENCH DECREE 321/2011	A+ Class

^{*} The final properties are obtained after 3-4 weeks, which is the time required for lime carbonation.

YIELD

The two-layer coating cycle implies a yield of approx. 1 m²/kg.

TENDER SPECIFICATION ITEM

"CARRARA MARBLE" EFFECT MINERAL COATING

Application with stainless steel float on treated surfaces of two layers of "carrara marble" mineral coating based on calcium hydrate and mineral extenders, as CREATIVE ARD LIME CARRARA, with an approximate consumption of 1,0 kg/m². €/ m².

The data herein were correct at the time of Quality Control and refer to standardized environmental conditions. The same are to be considered as a guide. 2023/03 revision

